



P8 PLUS

Flexible hose made of a layer of neoprene-coated fibreglass fabric, internal and visible copper steel wire helix and external fibreglass cord and external film for protection and reinforce.

TECHNICAL SPECIFICATIONS AND USAGE LIMIT

COLOR	LENGTH	WORKING TEMPERATURE	PRODUCTION DIAMETERS	AXIAL COMPRESSIBILITY	COMPLIANT TO FLAME RETARDANT STANDARDS
Black	4 m. standard	-55°C +130°C (peak +150°C)	from 22 to 305 mm	30%	Class M1 (UNE 23723- 90) CL V-0 (UL- 94)

PRODUCTION DIAMETERS

22	25	26	28	30	32	35	38	39	41	42	44	45	51	52	55	57	58	60	62	63	64	65	67	70
72	76	80	83	89	92	95	102	108	110	114	120	127	130	140	152	160	165	170	178	180	203	229	254	305

Diameters other than those indicated are available by prior feasibility check.

MAIN APPLICATIONS

Industrial suction and ventilation. Cooling of electronic equipments and ship machine rooms. Diesel air suction and motor vehicle heating. Particularly suitable for pneumatic lifting apparatus.

MAINTENANCE

Periodically check the state of wear of the hose and immediately replace it if damaged or broken. Pay maximum attention to the duct operating temperatures.

TECHNICAL DATA

DIAMETERS	OPERATING PRESSURE	OPERATING VACUUM	INSIDE CURVATURE RADIUS	WEIGHT
[mm]	[bar]	[mm H ₂ O]	[mm]	[gr/m]
25	1,60	5100	8	120
38	1,30	5000	12	168
51	1,20	4300	16	250
63	1,10	4000	20	300

DIAMETERS	OPERATING PRESSURE	OPERATING VACUUM	INSIDE CURVATURE RADIUS	WEIGHT
[mm]	[bar]	[mm H ₂ O]	[mm]	[gr/m]
76	1,10	3400	25	410
89	1,00	3000	29	490
95	0,90	2800	33	550
102	0,90	2600	35	650
114	0,90	2200	40	720
127	0,80	1700	46	800
152	0,70	1400	50	980
180	0,60	1100	60	1190
203	0,50	700	68	1330
254	0,40	450	100	1650
305	0,10	300	116	2000

The control pressure (expressed in bar*) is equal to the operating pressure by 1,5. The maximum pressure (expressed in bar*) is equal to the operating pressure by 3. Data given in this table are approximate. * Pressure and vacuum data based on +20°C room temperature.

GREEN BUILDING

Thanks also to the support of GreenMap, products manufactured by Tecnica srl contribute to obtain the credits of the major international rating systems for sustainable buildings:



LEED

Contributes to credits:

MR



WELL

Contributes to credits:

MATERIALS

For further details regarding the specific contributions to the credits indicated, contact Tecnica Srl.

APPLICATIONS

OEM	Working Temperature	Easy Pack	Industry	Extractor Hoods	High Temp. Suction	CMV Mech. Means