

P8 ISO

Flexible hose made of a layer of neoprene-coated fibreglass fabric, internal and visible copper steel wire helix and external fibreglass cord, with melamine insulation and external black neoprene anti-steam sheath.

TECHNICAL SPECIFICATIONS AND USAGE LIMIT									
COLOR	LENGTH	WORKING Temperature	PRODUCTION DIAMETERS	AXIAL COMPRESSIBILITY	COMPLIANT TO FLAME RETARDANT STANDARDS				
Black	3 m. standard	-55°C +130°C (peak +150°C)	from 25 to 254 mm	30%	Class M1 (UNE 23723-90) CL V-0 (UL-94)				

PRODUCTION DIAMETERS																	
25	30	32	35	38	39	41	44	45	51	55	57	60	63	64	70	80	83
89	95	102	114	120	127	140	152**	160**	178**	203**	254**						

**Hoses produced with a double layer of melamine. Diameters other than those indicated are available by prior feasibility check.

MAIN APPLICATIONS

Industrial suction and ventilation. Cooling of electronic equipments and ship machine rooms. Diesel air suction and motor vehicle heating.

MAINTENANCE

Periodically check the state of wear of the hose and immediately replace it if damaged or broken. Pay maximum attention to the duct operating temperatures.

TECHNICAL DATA									
DIAMETERS	OPERATING PRESSURE	OPERATING VACUUM	INSIDE CURVATURE Radius	WEIGHT					
[mm]	[bar]	[mm H ₂ O]	[mm]	[gr/m]					
38	1,30	5000	12	278					
51	1,20	4300	16	380					
63	1,10	4000	20	470					
76	1,10	3400	25	590					

DIAMETERS	OPERATING PRESSURE	OPERATING VACUUM	INSIDE CURVATURE Radius	WEIGHT
[mm]	[bar]	[mm H ₂ O]	[mm]	[gr/m]
89	1,00	3000	29	720
95	0,90	2800	33	790
102	0,90	2600	35	900
114	0,90	2200	40	980
127	0,80	1700	46	1100
152	0,70	1400	50	1410
180	0,60	1100	60	1670
203	0,50	700	68	1810
254	0,40	450	100	2295

The control pressure (expressed in bar*) is equal to the operating pressure by 1,5.

The maximum pressure (expressed in bar*) is equal to the operating pressure by 3.

Data given in this table are approximate.

GREEN BUILDING

Thanks also to the support of GreenMap, products manufactured by Tecnica srl contribute to obtain the credits of the major international rating systems for sustainable buildings:





LEED WELL

Contributes to credits:

MD

Contributes to credits:

MATERIALS

For further details regarding the specific contributions to the credits indicated, contact Tecnica Srl.

A P P L I C A T I O N S OEM Working Temperature Easy Pack Industry Extractor Hoods Suction Means *on request*



^{*} Pressure and vacuum data based on +20°C room temperature.